



2019

Nanomaterials

Birla Carbon's carbon black products include all ASTM, BC, CD, Conductex®, Copeblack®, PM, Raven®, and Ultra® grades.

The ASTM D3053 Standard on Terminology Relating to Carbon Black defines carbon black as follows:

Carbon black exhibits aciniform morphology composed of spheroidal "primary particles" strongly fused together to form discrete entities called aggregates¹. The primary particles are conceptual in nature, in that once the aggregate is formed the "primary particle" no longer exists, they are no longer discrete and have no physical boundaries amongst them. The aggregates are loosely held together by weaker forces forming larger entities called agglomerates. The agglomerates will break down into aggregates if adequate force is applied (e.g., shear force). Aggregates are the smallest dispersible unit¹. Carbon black is placed on the market in the form of agglomerates.

¹ The one exception to this general characteristic of manufactured carbon black involves thermal black, where "primary particles" can exist as discrete entities. However, "primary particles" produced via the thermal black process have characteristic diameters in the range of 150-500 nm, meaning that primary thermal black particles are of sizes that fall outside the nanoscale region.

Following the ASTM D3053 definition and applying the terminology of the International Organization for Standardization's (ISO) Technical Specification 80004-1 of 2010, carbon black is considered a nanostructured material (a material having internal or surface structure in the nanoscale).

The information presented within this publication is based on Birla Carbon's analysis and the analysis of others. Birla Carbon disclaims all representations and warranties regarding performance or use, express or implied, including implied warranties of merchantability and fitness for a particular purpose. The user is responsible for determining the suitability of any product for a specific purpose and the manner in which the product is used. Before handling, using, or processing any material, always read its Safety Data Sheet.

For additional information or for updates to this information, please email bc.hse@adityabirla.com or visit www.birlacarbon.com

Birla Carbon
1800 West Oak Commons Court
Marietta, Georgia 30062-2253, USA
+1 770 792 9400