



Raven and **Conductex**
Carbon Blacks for
Specialty Applications

FUNDAMENTAL PROPERTIES OF CARBON BLACK

A carbon black's application performance is determined by its fundamental properties and the level of dispersion achieved. The most important physical and chemical properties include particle size, porosity, structure, and surface chemistry. The level of dispersion in any given matrix is strongly influenced by the mixing equipment, formulation (including dispersant selection), and physical form.

PARTICLE SIZE is the primary influence on color properties. Particle size is measured by electron microscopy (EM). Mean particle size is certified via statistical thickness surface area (STSA) correlation according to ASTM D3849-14. Smaller particle diameter gives rise to higher surface area and tinting strength. High surface area is usually associated with greater jetness, higher conductivity, improved weatherability, and higher viscosity, but requires increased dispersion energy.


STRUCTURE is a measure of the three-dimensional fusion of carbon black particles to form aggregates. Highly structured carbon blacks provide higher viscosity, greater electrical conductivity and easier dispersion. Measures of aggregate structure may be obtained from shape distributions from EM analysis, oil absorption (OAN) or void volume analysis.





POROSITY is indicated by comparing a carbon black's external surface area predicted by STSA to the total surface area value obtained with the BET NSA method. Conductive carbon blacks tend to have a high degree of porosity.

SURFACE CHEMISTRY of carbon blacks generally refers to the oxygen-containing groups present on a carbon black's surface. Oxidized surfaces improve pigment wetting, dispersion, rheology, and overall performance in selected systems. In other cases, oxidation increases electrical resistivity and makes carbon blacks more hydrophilic. The extent of surface oxidation is measured by determining the quantity of the "volatile" component on the carbon black. High volatile levels are associated with low pH.

PHYSICAL FORM is important in matching a carbon black to the equipment by which it is to be dispersed. Powdered carbon blacks are recommended in low-shear dispersers and on three-roll mills. Beaded carbon blacks are recommended for shot mills, ball mills and other high energy equipment. Beading provides lower dusting, bulk handling capabilities, and higher bulk densities, while powdered carbon blacks offer improved dispersibility.

Carbon black particle showing Paracrystalline microstructure



PROPERTY	INFLUENCE OF PROPERTY ON PERFORMANCE
Particle Size Distribution 	Smaller Particle Size (Higher Surface Area) <ul style="list-style-type: none"> Increases Jetness Increases Tint Increases UV Protection Increases Electrical Conductivity Increases Resin Demand and Viscosity Reduces Dispersibility
Structure - Aggregate Size/ Shape Distribution 	Higher Structure (Increasing Oil Absorption) <ul style="list-style-type: none"> Reduces Jetness and Tint Improves Dispersibility Increases Resin Demand and Viscosity Increases Electrical Conductivity
Porosity - Pore Size Distribution 	Higher Porosity (Higher Ratio of NSA/STSA) <ul style="list-style-type: none"> Increases Resin Demand and Viscosity Increases Electrical Conductivity Enables Reduced Loadings in Conductive Applications
Surface Chemistry - Surface Functionality Distribution 	Higher Surface Functionality (Higher Volatile Content) <ul style="list-style-type: none"> Improves Resin Wetting Reduces Viscosity of Liquid Systems Lowers Electrical Conductivity

Additional Properties: • Other Constituents – Sulfur, Ash, Residue, etc. • Physical Form – Beads or Powder

Specialty blacks are used in a wide variety of applications including coatings, printing inks, plastics, and sealants. The selection of a specific product for an application depends on the end-use requirements as well as processing conditions.

ULTRA CARBON BLACKS

Birla Carbon products are high performance pigments targeted for use in demanding applications. Carbon black purity and consistency of performance, always important, are now recognized as being critical to continuing quality improvement. Birla Carbon has developed products that provide the highest level of purity available. These products, referred to as **Ultra** carbon blacks, serve as industry benchmarks in various application segments. **Ultra** products benefit various application systems by providing greater uniformity, increased compatibility, improved dispersion, better processing, longer screen life, enhanced color development, and reduced scrap.

COATINGS

Coatings may be formulated with an extremely wide range of products such as **Raven 410** for utility finishes, **Raven 1255** for various medium color industrial coatings, and **Raven 5000 Ultra II** for high quality, extremely jet, blue undertone automotive topcoat applications. Specialty blacks primarily used for tinting have low surface areas and broad particle size distributions. Products with these properties provide good economics coupled with a desired blue tone and best resistance to flooding and flocculation. **Raven 14** Powder, an easily dispersed post-treated carbon black, is the industry standard for blue undertone and tinting in paints and coatings.

INKS

Specialty blacks for inks are generally medium to coarse in particle size and are used for full color rather than tinting properties. In liquid ink applications such as publication and packaging gravure, the **Raven 400** and **Raven 500** series products are widely used because of their rheology, ease of dispersion, and blue tone. **Raven L Ultra** is used when the masstone requirements are higher. Depending on specific requirements, high quality inks are formulated with products such as **Raven 760 Ultra**, **Raven 1000**, and **Raven 1035**.

PLASTICS

Carbon black may be incorporated into thermosets or thermoplastics for color, tint, or functional reasons. Masstone color plastic applications can employ the entire available range of carbon black particle sizes. Selection will depend upon loading, dispersion, and cost. The coarser products are excellent choices in applications where blue tone, tinting strength, and ease of dispersion are preferred. **Conductex** blacks provide different degrees of electrical conductivity for a wide range of plastics requirements. **Conductex 7055 Ultra** and **Conductex K Ultra** offer optimum conductivity with minimal contribution to viscosity in applications such as wire and cable, ESD, as well as conductive coatings. For applications requiring very high jetness such as engineering plastics, **Raven 2000**, **Raven 2350 Ultra**, and **Raven 2500 Ultra** are recommended. For ultraviolet protection, **Raven UV Ultra** and **Raven PFEB** are industry standards for jacketing, film, and pipe applications.

GLOBAL SPECIALTY BLACKS PRODUCT PORTFOLIO

Raven and Conductex Carbon Blacks	D6556		D2414		D3265	2A-700	Typical Applications
	NSA Surface Area m ² /g	STSA Surface Area m ² /g	OAN Oil Absorption cm ³ /100g		Tinting Strength	Volatile Content %	
			Beads	Powder			
Raven 5100 Ultra	583	350	75	95	135+ ²	-	Automotive topcoat, architectural coatings; piano black plastics applications
Raven 5000 Ultra II ¹	583	350	95	95	135+ ²	10.5	
Raven 5000 Ultra 3 ¹	583	350	95	95	135+ ²	10.5	
Raven 3500 ¹	375	212	105	105	135+ ²	5.0	
Raven 3000 Ultra	260	235	70	73	135+ ²	-	High jetness plastics; industrial and powder coatings; inkjet ink
Raven 2900 Ultra	254	215	65	67	135+ ²	-	
Raven 2800 Ultra	257	205	95	100	135+ ²	-	
Raven 2500 Ultra	270	206	65	67	135+ ²	-	
Raven 2350 Ultra	195	180	60	62	135+ ²	-	
Raven 2000	194	168	65	70	135+ ²	-	
Raven 1255 ¹	122	119	66	66	135	2.7	Premium offset ink, UV ink and specialty coatings
Raven 1250	113	102	55	60	128	-	Coatings, plastics, inks
Raven 1200	106	104	55	60	128	-	
Raven 1190 Ultra	113	100	57	-	125	-	Inks, coatings, and fiber
Raven 1185 Ultra ¹	100	97	-	100	124	2.5	Specialty coatings; high quality inks including offset, packaging, UV, inkjet, toner
Raven 1180 ¹	110	97	-	60	128	2.7	
Raven 1170	107	101	55	60	124	-	Inks, coatings, and plastics
Raven 1100 Ultra ¹	101	95	72	72	120	2.4	High quality inks including heatset, sheetfed, UV, and packaging; coatings
Raven 1080 Ultra ¹	79	77	60	60	109	1.6	
Raven 1060 Ultra ¹	66	65	50	50	102	1.6	
Raven 1040 ¹	90	86	100	100	115	2.6	
Raven 1035 ¹	91	91	65	65	125	2.4	
Raven 1020	95	90	58	60	121	-	Inks, coatings, and plastics
Raven 1010	95	91	-	58	126	-	
Raven 1000	92	91	58	63	126	-	
Raven 900	82	81	-	108	102	-	
Raven 880	78	76	102	-	102	-	Geomembrane, film, and molding
Raven 880 Ultra	78	76	102	-	102	-	
Raven 860 Ultra	48	48	48	50	91	-	High quality inks including heatset, sheetfed, and packaging
Raven 850	63	63	-	75	101	-	Coatings, inks, and plastisol
Raven 820	73	71	120	-	100	-	Flexographic ink
Raven 790 Ultra	64	64	-	105	95	-	Sealants
Raven 780 Ultra	89	77	58	60	109	-	Toner and specialty inks
Raven 760 Ultra	64	64	48	50	102	-	High quality inks including heatset, sheetfed, and packaging; coatings
Raven 675 Ultra	69	68	45	-	97	-	
Raven 525	43	42	121	-	55	-	Plastic color concentrate for film, pipe, and molding
Raven 520	40	39	121	-	58	-	
Raven 520 Ultra	40	39	121	-	58	-	
Raven 510 Ultra	38	38	90	-	57	-	

GLOBAL SPECIALTY BLACKS PRODUCT PORTFOLIO (CONTINUED)

Raven and Conductex Carbon Blacks	D6556		D2414		D3265	2A-700	Typical Applications
	NSA Surface Area m ² /g	STSA Surface Area m ² /g	OAN Oil Absorption cm ³ /100g		Tinting Strength	Volatile Content %	
			Beads	Powder			
Raven 500	44	44	75	80	69	-	Plastic color concentrate for film and molding; blue undertone and tinting in coatings
Raven 450	35	34	63	65	61	-	
Raven 435	35	34	90	-	62	-	
Raven 430 Ultra	31	31	75	78	58	-	
Raven 425	29	29	72	75	54	-	
Raven 420	28	28	72	75	50	-	
Raven 410	26	26	65	68	47	-	
Raven 415	32	32	65	-	61	-	News ink and plastic color concentrate
Raven 415 Ultra	32	32	65	-	61	-	
Raven 22	28	27	-	113	44	-	Blue undertone and tinting in coatings; solid carbon and metallurgical
Raven 16	30	29	-	105	46	-	
Raven 14¹	44	44	-	111	66	1.7	Blue undertone and tinting in coatings
Raven FC1	115	100	100	-	112	-	U.S. FDA 21 CFR 178.3297 indirect food-contact plastics
Raven L	85	85	72	78	110	-	Inks, coatings, and plastics <i>Note: Raven L bead is produced in Korea only</i>
Raven L Ultra	85	85	72	-	110	-	
Raven M	78	76	102	-	102	-	Conductive and film
Raven P	155	109	113	-	107	-	
Raven P5	109	100	-	117	115	-	Sealant, pipes, film, and fiber
Raven P5 Ultra	109	100	112	117	115	-	
Raven P7 Ultra	90	85	98	-	105	-	Pipe, film, and fiber
Raven P125 Ultra	71	70	100	-	92	-	Pipe, film, and geomembrane
Raven PFEB	107	91	98	-	105	-	Pipe, film, and fiber
Raven SF8 Ultra	125	100	114	-	114	-	Fine denier synthetic fibers
Raven UV Ultra	124	112	114	-	118	-	UV protection, cable jacketing, and fiber
Conductex SC Ultra	205	124	115	115	123	-	Wire and cable, ESD, and other conductive applications
Conductex K Ultra	185	125	141	-	115	-	
Conductex 7097 Ultra	85	82	160	-	97	-	
Conductex 7093	75	73	140	-	98	-	
Conductex 7067 Ultra	63	54	140	-	65	-	
Conductex 7060 Ultra	63	56	156	-	70	-	
Conductex 7055 Ultra	55	50	170	-	61	-	
Conductex 7051 Ultra	43	42	121	-	55	-	Wire and cable insulation shield
Conductex 7054 Ultra	43	42	122	-	60	-	
Conductex 7090	43	42	121	-	55	-	
Conductex 7095 Ultra	39	39	121	-	58	-	

Rev 05/2021

1 - Surface oxidized, "Treated" product
Treated products typically range in pH from 3.0-3.5
Non-treated products typically range in pH from 6.5-8.0
OAN and tint strength are measured prior to treatment

2 - The ASTM Tinting Strength value for high surface area products plateaus at about 135% ITRB, consequently ASTM Tinting Strength is not indicative of performance for this range of products.

Color Index No. 77266, Pigment Black 7, CAS No. 1333-86-4

ABOUT BIRLA CARBON


Birla Carbon is one of the world's largest manufacturers and suppliers of high quality carbon black and a flagship business of the Aditya Birla Group. Our contemporary research infrastructure and state-of-the-art technology centers provide carbon black solutions to leading companies in the rubber and specialty applications sectors worldwide.

As an ardent practitioner of sustainable development, Birla Carbon's Sustainable Operational Excellence (SOE) strategy focuses on employee safety, environmental stewardship, efficient use of carbon sources and a key focus on conducting operations

in a socially and ethically responsible manner. In 2020, Birla Carbon was awarded a Gold level rating for sustainable practices for the fifth consecutive year by EcoVadis.

Birla Carbon's Purpose, Share the Strength, is about balanced and shared leadership, working at the product level to innovate cutting edge solutions, through collaboration with its people, customers and communities and backed by knowledge built over a century.

For more information, visit birlacarbon.com, or follow us @BirlaCarbon on Twitter, LinkedIn, Facebook, or Instagram.



SHARE THE STRENGTH

NORTH AMERICA

Birla Carbon U.S.A., Inc.
1800 West Oak Commons Court
Marietta, Georgia 30062-2253 USA
Phone: +1 770 792 9400

SOUTH AMERICA

Birla Carbon Brazil Ltda.
Rua Guaiaó, 66 –
Salas 1012 a 1016 –
Bairro Aparecida
Santos, Brazil 11035-260
Phone: +55 13 3279 1300

EUROPE, MIDDLE EAST, AFRICA

Birla Carbon Europe GmbH
Podbielskistrasse 160 D-30177
Hannover
Germany
Phone: +49 511 630 890

ASIA/INDIA

Birla Carbon India Private Limited
910/911, Kailash Building
Kasturba Gandhi Marg
New Delhi – 110 001
India
Phone: +91 11 2335 1069 / 2335 1070

ASIA/THAILAND

Birla Carbon (Thailand) Public
Co. Ltd.
888/122, 888/128, Mahatun Plaza,
12th Floor, Ploenchit Road,
Lumpini
Pratumwan, Bangkok 10330
Thailand
Phone: +66 2253 6745

ASIA/CHINA

Birla Carbon China (Jining) Co. Ltd.
6th, Chenguang Road,
Jibe High Tech Development Zone
Jining City, Shandong Province
China 272000
Phone: +86 177 5371 2538

ASIA/SOUTH KOREA

Birla Carbon Korea Co., Ltd.
7th Floor Taewoo Building
285 Gangnamdae-ro Seocho-gu
Seoul 137 070

ADITYA BIRLA



BIRLA CARBON

BIRLACARBON.COM



GET THE APP

The information presented within this publication is based on Birla Carbon's research and the research of others, but neither its accuracy nor completeness is guaranteed. BIRLA CARBON MAKES NO, AND DISCLAIMS ALL, REPRESENTATIONS AND WARRANTIES, EXPRESS OR IMPLIED, REGARDING ACCURACY, PERFORMANCE, STABILITY, RELIABILITY, OR USE, INCLUDING IMPLIED WARRANTIES OF MERCHANTABILITY AND OR FITNESS FOR A PARTICULAR PURPOSE. The user is solely responsible for determining the suitability of any product for a specific purpose. No suggestion for use is intended as or should be construed as a recommendation to infringe upon any patent or to violate any law or regulation. Before handling, using, or processing any material, always read its Material Safety Data Sheet.

©2021 Birla Carbon